



DUNBAR – 1635S

2:1 SHRINK RATIO, SEMI-RIGID, FLAME RETARDANT, POLYOLEFIN TUBING

Applications

DUNBAR-1635S is designed for wire strain-relief applications and terminations, wire splices, soldered or crimped connections. It provides tough and high abrasion resistance for delicate components in mechanical environments.

Features

- ★ Shrink ratio: 50% or more in the radial direction, 5% or less in the axial direction
- ★ In stock for immediate shipments (Black, Clear, and Optional Colors)
- ★ Continuous operating temperature: - 55 °C (-67 °F) to 135 °C (275 °F)
- ★ Flammability: ASTM D2671 procedure B
- ★ High resistance to abrasion, chemicals and oils

Standard

- ★ AMS-DTL-23053/6 Class 1, Class 2 is Clear (Formerly MIL-DTL-23053/6 Class 1 & 2)
- ★ RoHS Compliant

Specification Values


Property		Test Method	Value
Physical	Unaged	Tensile strength	ASTM D638 Min. 2,000 psi
		Elongation	Min. 200%
	Aged	Elongation	ASTM D638 Min. 100%
	Fluid Resist.	Tensile strength	24 °C/24 hrs Min. 1,600 psi
		Dielectric strength	6 Fluids Min. 400 Volts/mil
	Concentricity		ASTM D2671 Min. 70%
	Heat shock		250 °C/4 hrs No cracks, flowing or dripping
	Low temperature flexibility		- 55 °C/4 hrs No cracking
	Secant modulus		ASTM D882 Min. 25,000 psi
Specific gravity		ASTM D792 Max. 1.35 (Max. 1.00 Clear)	
Electrical	Dielectric strength		ASTM D2671 Min. 500 Volts/mil
	Volume resistivity		ASTM D876 Min. 10 ¹⁴ Ω - cm
Chemical	Copper corrosion		150 °C/16 hrs No corrosion
	Fungus resistance		ASTM G21 No growth
	Water Absorption		ASTM D570 Max. 0.5% (Max. 0.2% Clear)
	Flammability		ASTM D2671 Pass

Rev. Feb 2015



DUNBAR – 1635S

2:1 SHRINK RATIO, SEMI-RIGID, FLAME RETARDANT, POLYOLEFIN TUBING



Fully recovered after heating

Product Dimensions

Minimum Shrink Temperature: 130°C

Size	Expanded		Recovered				Standard Spool Length
	Internal Diameter Minimum (D)		Internal Diameter Maximum (d)		Total Wall Thickness Minimum (t)		
Inch Size	In.	mm	In.	mm	In.	mm	Ft.
3/64"	0.047	1.2	0.023	0.58	0.013	0.33	500
1/16"	0.063	1.6	0.031	0.79	0.014	0.36	500
3/32"	0.094	2.4	0.046	1.17	0.017	0.43	500
1/8"	0.126	3.2	0.062	1.57	0.017	0.43	500
3/16"	0.189	4.8	0.093	2.36	0.017	0.43	250
1/4"	0.252	6.4	0.125	3.18	0.022	0.56	250
3/8"	0.378	9.6	0.187	4.75	0.022	0.56	200
1/2"	0.500	12.7	0.250	6.35	0.022	0.56	200
3/4"	0.752	19.1	0.375	9.53	0.027	0.69	100
1"	1.0	25.4	0.5	12.70	0.030	0.76	100

Rev. Feb 2015



Dunbar Products, LLC
Tubing and Identification Products

1302 Champion Circle, Carrollton, TX 75006
Tel: (469) 568-0800
Fax: (469) 568-0808